

CLAIMS

1. Powdery water-absorbing polymers comprising as components:

- 5
- 0.01 to 20 wt.% of a fine particle with a particle size of less than 200 μm ,
 - 0.001 to 10 wt.% of a thermoplastic adhesive,
 - 60 to 99.998 wt.% of a water-absorbing polymer particle with a particle size of 200 μm and above,

wherein

10 the fine particles are bound to the surface of the water-absorbing polymer particles by the thermoplastic melt adhesive and the powdery water-absorbing polymers have either

- a flow value (FFC) within the range from 1 to 13, or
- a dust portion of at most 6.

15

2. Powdery water-absorbing polymers according to claim 1, with a flow value (FFC) in the range from 1 to 13 and a dust portion of at most 6, respectively based on the total weight of the powdery water-absorbing polymers.

20 3. Powdery water-absorbing polymers according to claim 1 or 2, wherein the thermoplastic adhesive has a melt temperature according to ISO 11357 of at least 50°C, preferably of at least 60°C and even more preferably of at least 70°C.

25 4. Powdery water-absorbing polymers according to any one of the preceding claims, wherein the thermoplastic adhesive has a melt viscosity according to Brookfield (ASTM E 28) with a number 27 spindle at a temperature of 160°C of less than 2000 Pas.

5. Powdery water-absorbing polymers according to any one of the preceding claims, wherein the thermoplastic adhesive comprises a polycondensate to at least 10 wt.%, preferably at least 50 wt.% and particularly preferably at least 90 wt.%.
5
6. Powdery water-absorbing polymers according to claim 5, wherein the polycondensate is a polyester.
10
7. Powdery water-absorbing polymers according to any one of the preceding claims, wherein the fine particle comprises an organic fine particle to at least 80 wt.%, based on the weight of the fine particle.
10
8. Powdery water-absorbing polymers according to any one of the preceding claims, wherein the fine particle comprises an inorganic fine particle to at least 80 wt.%, based on the weight of the fine particle.
15
9. Powdery water-absorbing polymers according to any one of the preceding claims, wherein these are secondary cross-linked in the surface region by means of a surface cross-linker.
20
10. Powdery water-absorbing polymers according to claim 9, wherein the surface cross-linker comprises at least one organic compound or at least one polyvalent metal cation.
25
11. Powdery water-absorbing polymer comprising to at least 30 wt.% a cross-linked, partially neutralized, preferably neutralized in the range of 60 to 80 mol.%, polyacrylic acid and with at least one of the following properties
25
- P1 a flow value (FFC) within the range of 1 to 13; or
 - P2 a dust portion of at most 6,
 - P3 an attrition index A_i within the range of 1 to 17;
 - 30 P4 an attrition difference A_d within the range of 0 to 7,

P5 a retention determined according to ERT 441.1-99 of at least 20 g/g.

12. Process for producing powdery water-absorbing polymers, wherein as components:

- 5 - 0.01 to 20 wt.% of a fine particle with a particle size of less than 200 μm ,
- 0.001 to 10 wt.% of a thermoplastic adhesive,
- 60 to 99.998 wt.% of a water-absorbing polymer particle with a particle size of 200 μm and above,
- 10 are brought into contact with each other at a temperature within the range of 120 to 250°C, preferably 150 to 220°C and particularly preferably 170 to 200°C.

13. Process according to claim 12, wherein the bringing into contact occurs in a continuously conveying mixing oven.

15

14. Process according to claim 13, wherein the oven has movable, heated conveying means.

15. Process according to any one of claims 12 to 14, wherein as further
20 component a secondary cross-linker is brought into contact.

16. Process according to claim 15, wherein the secondary cross-linker and the thermoplastic adhesive are conducted together to the other components.

25 17. Process according to claim 15 or 16, wherein at least the secondary cross-linker is present in a liquid phase.

18. Powdery water-absorbing polymers, obtainable by a process according to any one of claims 12 to 17.

19. Powdery water-absorbing polymers according to claim 18 with at least one of the properties P1 to P5 defined in claim 11.

5 20. Powdery water-absorbing polymers according to any one of claims 1 to 11, 18 or 19, wherein at least 50 wt.% of the powdery water-absorbing polymers have a particle size within the range of greater than 50 to 2,000 μm .

 21. Transport process, wherein powdery water-absorbing polymers according
10 to any one of claims 1 to 12, 18 or 19 flow through a channel.

 22. Process according to claim 21, wherein the channel forms part of an installation for producing a water-absorbing polymer or of a dosing system for a water-absorbing polymer.

15

 23. Composite, comprising powdery water-absorbing polymers according to any one of claims 1 to 12, 18 or 19.

 24. Chemical products, comprising powdery water-absorbing polymers
20 according to any one of claims 1 to 12, 18 or 19.

 25. Use of a thermoplastic adhesive for alteration of the flow value (FFC) or the dust portion in powdery water-absorbing polymers comprising this thermoplastic adhesive with respect to powdery water-absorbing polymers not comprising this
25 thermoplastic adhesive.